

Technical Properties of:		ZELLAMID® 900 (POM-C)			
Edition / Date:		2 / 01-01-2016			
Characteristics	Unit	Test method	Condition of specimen	Value	
MECHANICAL PROPERTIES					
Yield stress	23 °C	MPa	ISO 527	65	
Tensile strength	23 °C	MPa	ISO 527	65	
Elongation at break	23 °C	%	ISO 527	40	
Tensile E-Modulus		MPa	ISO 527	2 900	
Bending Modulus		MPa	ISO 178	2 800	
Flexural Strength		MPa	ISO 178	95	
Charpy impact strength	23 °C	kJ/m ²	ISO 179/1eU	no break	
Charpy Notched Impact Strength	23 °C	kJ/m ²	ISO 179/1eA	7	
Shore D hardness			ISO 868	81	
Ball Hardness		MPa	ISO 2039-1	125	
Compressive modulus		MPa	ISO 604	2 400	
Compressive Stress	1 % Nominal Strain	MPa	ISO 604	23	
	2 % Nominal Strain	MPa	ISO 604	44	
	5 % Nominal Strain	MPa	ISO 604	82	
THERMAL PROPERTIES					
HDT-A	1,82 MPa	°C	ISO 75	110	
Glass Transition Temperature		°C	ISO 3146	-60	
Melting Temperature		°C	ISO 3146	164	
Maximum Service Temperature for Few Hours Operation		°C	-	140	
Service temperature long term		°C	-	100	
Minimum service temperature		°C	-	-50	
Specific Heat Capacity		J/(g.K)	IEC 1006	dry 1.5	
Coefficient of thermal expansion		1/K10 ⁻⁵	DIN 53752	11	
Thermal Conductivity	Method A	W/(K.m)	-	dry 0.336	
DIELECTRIC PROPERTIES					
Dielectric Constant	1 MHz		IEC 60250	3.8	
Dissipation Factor Tan δ	1 MHz		IEC 60250	0.005	
Dielectric Strength		KV/mm	IEC 60243	> 20	
Volume Resistivity		Ω.cm	IEC 60093	10 ¹⁴	
Surface Resistivity		Ω	IEC 60093	10 ¹³	
Resistance to Tracking (CTI)			IEC 60112	600	
PHYSICAL PROPERTIES					
Density	23 °C	g/cm ³	ISO 1183-1	1.41	
BURNING BEHAVIOUR					
Flammability classification*			UL 94	HB	
GENERAL					
Water Absorption	23 °C, saturation	%	ISO 62	0.8	
	23 °C / 50% RH	%	ISO 62	0.2	
Food contact approval			FDA	+	
Dimensional Stability			-	+	
Coefficient of Friction			-	+	
Wear Resistance			-	-	
RESISTANCE					
Chemical Resistance			-	+	

Resistance to wear tested by a pin / rotating disc test according DIN ISO 7148-2 under following conditions: Ra = 0.35 - 0.45 µm (steel disc), v = 0.3 m/s, p = 3 N/mm², time T > 16 h

Explanation Symbols: + good 0 neutral - not good / actually not available

Tests are done under dry conditions at room temperature

All statements, technical information and recommendations contained in this data sheet are presented in good faith, but all information given is without warranty and liability. Properties of the delivered products can vary because of differences to the testing samples. Non-tested values are fulfilled with raw material datas and literature information. The reader is cautioned, however that Zell-Metall cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine the suitability of Zell-Metall products in any given application.